



Solution welding compound

For homogenous wind and water-tight welding of Omega UDOs 330 roofing membrane.

FIELD OF APPLICATION

- for homogenous wind and water-tight welding of Omega UDOs 330 roofing membrane

ADVANTAGES

- one-component
- contains solvent
- ready for use

RECOMMENDED ACCESSORIES



Bottle with brush

AVAILABLE IN THE FOLLOWING DIMENSIONS

Container size / Can	1 litre
----------------------	---------

PRODUCT DATA

Composition	tetrahydrofuran
Density	0,89 g/cm ³
Working temperature	from ca 5°C
Coverage	ca. 7ml / lfm
Form	liquid
Storage	at room temperature
Solvent content	organic solvent 99,9 %

GUIDELINES FOR USE

Apply the solution welding compound using the bottle with brush (min. 4cm welding seam). Immediately place the overlapping sheets on top of each other and press on lightly with the back of the hand. Without delay press on firmly at right angles to the direction of the seam using a roller (to prevent formation of folds).

Observe safety instructions! We recommend that protective goggles are worn during work.

INFO :
+43 6216 / 4108
WWW.ISOCELL.COM

ISOCELL